

522-M0

Variant 523-15



A brand of BASF –
We create chemistry

Application:

Key Features:

- Reduction of drying times
- Improves surface drying and curing performance as well as tape resistance

		2:1+10 %			
	Mixing Ratio	100 % by volume	522-M0		
	Hardener	50 % by volume	929-91, -93		
	Reducer	10 % by volume	523-15		
	Spray viscosity at 20°C	DIN 4:	20-24 s	Potlife at 20°C	30 min

Application:	Compliant gravity-feed spray gun	HVLP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.3-1.4 1.3
Number of spray coats		2
Flash off at 20°C	min	intermediate flash-off app. 5 min.
Film thickness	µm	50-70
Application Remark	Alternatively: 1/2 + 1 spray coat can be applied to vertical surfaces no flash-off between coats required. (approx. 50 µm)	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

522-M0

Variant 523-15



A brand of BASF –
We create chemistry



Drying at 20°C 4 h

Drying at 60°C 15 min



Infrared (short wave) 6 min

Infrared (medium wave) 8-12 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.