








Glasurit® Etch Primer Filler

G / P

- Application:** Primer
- Properties:** Very good anti-corrosive properties
- Remarks:** **For steel, aluminium and galvanised steel.**
Do not recoat with polyester body filler!
Do not use under 176-72!
Can be used as primer with 352-228 Glasurit Activator, too. See Technical Information 283-150 in chapter G / PF.
Not recoatable with 90 Line!

	Application	Primer
	Mixing ratio	1 : 1 100% by vol. 283-150
	Hardener	100% by vol. 352-230
	Reducer	
	Potlife at 20 °C	7 days
	Spray viscosity DIN 4 at 20°C	15 s
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.3 - 1.8 mm 2.0 – 3.0 bar 0.7 bar at the nozzle Compliant gravity-feed spray gun: 1.3 -1.8 mm 2.0 bar
	Number of spraycoats	1-2
	Film thickness	10-15 µm
	Flash-off at 20°C	ca. 10 min.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c III)(780)760: The EU limit value for this product (product category: IIB.c III) in ready to use form is max 780 g/litre of VOC. The VOC content of this product is 760 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

