

# 151-190E Eco Balance

UV primer filler, dark grey



A brand of BASF –  
We create chemistry

**Application:** Primer filler for metal  
**Key Features:** Suitable for steel, galvanized steel and aluminium.  
 Good corrosion resistance, excellent topcoat holdout.



## Paint System

The material is ready for use.

## Handling



Material should not be stirred.  
 Shake vigorously for 2 min. before each use.



Do not apply in direct sunlight.  
 Do not expose to sunlight in storage



**Spray viscosity at 20°C**    DIN 4:    18-20 s    **Potlife at 20°C**

## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c II)(540)540:** The EU limit value for this product ( product category: IIB.C II ) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 151-190E Eco Balance

UV primer filler, dark grey



A brand of BASF –  
We create chemistry

Application:	Compliant gravity-feed spray gun	HVLSP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.1-1.2

**Number of spray coats** ½ + 1  
 151-190E Eco Balance appears transparent and should not be sprayed to cover. If higher film builds are necessary, a second layer 151-190E Eco Balance can be applied with intermediate sanding after having cured the first layer.  
 Film builds rapidly with this product, do not spray to cover. Do not apply more than 1.5 coats per layer.

**Flash off at 20°C** min  
 20 s between the first and the second coat.  
 If spraycoats are applied too wet, a longer intermediate flash off between coats and curing is recommended.

**Film thickness** µm  
 max. 120 per layer



**UV Curing**

5 min. (UV-A > 6 mW/ cm<sup>2</sup>)  
 By using LED lamps, the curing time can be reduced due to their higher intensity in the decisive wavelength range. This must be checked individually.



**Sanding manual, wet**

P800



**Orbital sanding, dry**

P400 - P500

**Safety advice:**

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c II)(540)540:** The EU limit value for this product ( product category: IIB.C II ) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# 151-190E Eco Balance

UV primer filler, dark grey



A brand of BASF –  
We create chemistry



## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c II)(540)540:** The EU limit value for this product ( product category: IIB.C II ) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

06/2020