

### Glasurit® Primer Filler Pro, white

# G / PF

- Application:** Primer filler / wet-on-wet filler
- Properties:** Suitable for steel, galvanized steel, aluminium, old paintwork and GRP / SMC  
Good corrosion protection and weathering resistance, good finish quality
- Remarks:**
- Use 581-90 Glasurit Guide Coat, black as guide coat (for a better sanding result).
  - To create different shades of grey, 285-230 Glasurit Primer Filler Pro white and 285-290 black can be mixed. (See Glasurit Filler Grey Shade Concept).
  - No need to sand new e-coated parts.
  - Parts coated with 285-230 can be overcoated without intermediate sanding for up to 5 days
  - **Clean the surface with 700-10 Glasurit Degreasing and cleaning agent before applying 285-230.**
  - Minimum temperature for air drying: +15°C.

#### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.












**2004/42/II B(c I)(540)539:** The EU limit value for this product ( product category: IIB.c II )in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



### Glasurit® Primer Filler Pro, white

# G / PF

	Application	Primer Filler			
	<b>Spreading rate</b>	m <sup>2</sup> / l at 1 µm			
	<b>Mixing ratio</b>	<b>5 : 1 : 1 for metal</b> 100% by vol.	285-230	<b>5 : 1 : 1 for plastics</b> 100% by vol.	285-230
	<b>Hardener</b>	20% by vol.	929-58	20% by vol.	929-58
	<b>Reducer</b>	20% by vol.	352-91, -50, -216, 352-30, -40, -10	20% by vol.	522-10
	<b>Spray viscosity DIN 4 at 20°C</b>	18 – 20 s			
	<b>Potlife at 20 °C</b>	90 min			
	<b>Gravity cup Spraying pressure</b>	HVLP spray gun: 1.7 – 1.9 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle		Compliant gravity-feed spray gun 1.6 – 1.8 mm, 2.0 bar	
	<b>Number of spraycoats</b>	½ + 1			
	<b>Film thickness</b>	50 – 70 µm			
	<b>Drying at 20 °C</b>	16 h			
	<b>Drying at 60 °C</b>	for 35 min			
	<b>Infrared (short wave)</b>	9 min (4 min. 60 °C, 5 min. 80 °C)			
	<b>Sanding: manual</b>	P800			
	<b>Sanding: orbital sander</b>	P400 - P500			

#### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.








**2004/42/II B(c I)(540)539:** The EU limit value for this product ( product category: IIB.c II )in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



### Glasurit® Primer Filler Pro, white

# G / PF

	Application	Wet-on-Wet Filler for metal		Wet-on-Wet Filler for plastics		
	<b>Spreading rate</b>					m <sup>2</sup> / l at 1 µm
	<b>Mixing ratio</b>	<b>4 : 1 : 1</b> 100% by vol.	285-230	<b>4 : 1 : 1</b> 100% by vol.	285-230	
	<b>Hardener</b>	25% by vol.	929-58	25% by vol.	929-58	
	<b>Reducer</b>	25% by vol.	352-91, -50, -216, 352-30, -40, -10	25% by vol.	522-10	
	<b>Spray viscosity DIN 4 at 20°C</b>	15 – 20 s				
	<b>Potlife at 20 °C</b>	90 min				
	<b>Gravity cup Spraying pressure</b>	HVLP spray gun: 1.3 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle		Compliant gravity-feed spray gun 1.3 – 1.4 mm, 2.0 bar		
	<b>Number of spraycoats</b>	$\frac{1}{2} + 1 = \frac{1}{2} \times \text{putty area} / 1 \times \text{whole area}$		<b>Film thickness:</b> app. 30 - 40 µm		
	<b>Flash-off at 20°C</b>	25 - 30 min				

#### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.












**2004/42/II B(c I)(540)539:** The EU limit value for this product ( product category: IIB.c II )in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



### Glasurit® Primer Filler Pro, white

# G / PF

	Application	High-build primer filler	
	Spreading rate	m <sup>2</sup> /l at 1 µm	
	Mixing ratio	<b>5 : 1 : 1</b> 100% by vol.	285-230
	Hardener	20% by vol.	929-58
	Reducer	20% by vol.	352-91, -50, -216, 352-30, -40, -10
	Spray viscosity DIN 4 at 20°C	18 – 20 s	
	Potlife at 20 °C	90 min	
	Gravity cup Spraying pressure	HVLP spray gun: 1.7 – 1.9 mm 2.0 – 3.0 bar /0.7 bar at the nozzle	Compliant gravity-feed spray gun 1.6 –1.8 mm 2.0 bar
	Number of spraycoats	½ + 2	
	Film thickness	80 – 120 µm	
	Flash-off at 20°C	-	
	Drying at 20 °C Drying at 60 °C	16 h 45 min	
	Infrared (short wave)	15 min (4 min. 60 °C, 11 min. 80 °C)	
	Sanding: manual	P800	
	Sanding: orbital sander	P400 - P500	

#### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/II B(c I)(540)539:** The EU limit value for this product ( product category: IIB.c II )in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

