

285-270

Primer Filler Pro, grey variant Wet-on-Wet Filler for metal



A brand of BASF –
We create chemistry

Application: Wet-on-wet filler

4:1:1



Mixing Ratio

100 % by volume

285-270



Hardener

25 % by volume

929-58



Reducer

25 % by volume

352-10, -30, -50, -40, -216, -91



Spray viscosity at 20°C

DIN 4:

15-20 s

Potlife at 20°C

90 min

Application:



**Compliant gravity-feed
spray gun**



HVLP spray gun

Application pressure bar

2

2-3

Nozzle pressure bar

0.7

Nozzle size

1.3-1.4

1.3

Number of spray coats

$\frac{1}{2} + 1 = \frac{1}{2} \times \text{putty area} / 1 \times \text{whole area}$

Flash off at 20°C min

25-30

Film thickness µm

30-40

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II(c I)(540)539: The EU limit value for this product (product category: IIB.c I)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.