

Glasurit® HS Primer Filler, grey

G / PF

- Application:** Efficient HS primer filler with excellent wet and dry sanding properties
- Properties:** High solids content; fast drying; good corrosion protection, good weathering resistance and good finish
- Remarks:**
- 285-505 corresponds to grey shade of 285-.../03
 - 285-505 can be mixed with Glasurit HS Primer Fillers 285-555 black and 285-655 white to achieve different grey shades.
 - You can add 523-15 Glasurit Racing Additive (see technical data sheet of 523-15) to accelerate the drying process of 285-505
 - Use 581-90 as guide coat (for a better sanding result)

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.












2004/42/II B(c II)(540)539: The EU limit value for this product (product category: IIB.C II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Glasurit® HS Primer Filler, grey

G / PF

	Paint system	RATIO Aqua, RATIO HS	
		Spreading rate: 425 m ² /l at 1 µm	
	Mixing ratio	4 : 1 : 1 100 % by vol.	285-505
	Hardener	25 % by vol.	929-55, -56
	Reducer	25 % by vol.	352-91, -50, -216 352-30, -10, -40
	Spray viscosity DIN 4 at 20°C	18 – 22 s	Potlife 20°C 1 h
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.7 – 1.9 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	Compliant gravity-feed spray gun: 1.6 – 1.8 mm 2.0 bar
	Number of spraycoats	2 Flash-off between spraycoats until mat, no flash-off before drying.	
	Film thickness	50 – 70 µm	
	Drying at 20 °C Drying at 60 °C	3 h 20 min.	
	Infrared (short wave) Infrared (medium wave)	9 min. 10 – 15 min.	
	Sanding: manual	P800	
	Sanding: orbital sander	P400 - P500	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c II)(540)539: The EU limit value for this product (product category: IIB.C II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

