285-700

Primer Filler, grey



Application:

Primer filler.

Key Features:

Excellent spray ability, sagging resistance and filling properties.

Wet and dry sanding properties.

Remarks:

Use 581-90 Glasurit Guide Coat, black as guide coat (for a better sanding result).

285-700 can be mixed with Glasurit 523-15 Racing Additive to reduce the drying time (to 15 min at 60°C, 1.5h at 20°C or 6 min with short-wave infrared). Please observe that the mixture has a potlife of

only 20 min at 20°C and can only be used for applying film thicknesses of 50-70 µm.



Spreading rate

425 m²/l at 1 µm

4:1:1



Mixing Ratio

100 % by volume

285-700



Hardener

25 % by volume

929-55, -56



Reducer

25 % by volume

352-91, -50, -30, -40, -10, -216



Spray viscosity at 20°C

DIN 4:

20-24 s

Potlife at 20°C

1 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

285-700

Primer Filler, grey



Applicati	on:		spray gun	+++ HVLP spray gun
Application pressure bar			2	2-3
Nozzle pressure bar				0.7
Nozzle size			1.6-1.8	1.7-1.9
Number of spray coats				2
Film thickness µm			!	50-70
	Drying at 20°C	3 h		
Ü	Drying at 60°C	30 min		
\bigcirc	Infrared (short wave)	9 min		
'IR'	Infrared (medium wave)	10-15 min		
	Sanding manual, wet			P800
S.	Orbital sanding, dry		P40	0 - P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must

Compliant gravity-feed

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

always be observed in addition to the processing instructions given within this document.