

285-730

Primer Filler, white variant High-build primer filler



A brand of BASF –
We create chemistry

Application: Primer filler.



Spreading rate 425 m²/l at 1 µm

4:1:1



Mixing Ratio 100 % by volume 285-730



Hardener 25 % by volume 929-55, -56



Reducer 25 % by volume 352-50, -91, -216, -30, -40, -10



Spray viscosity at 20°C DIN 4: 20-24 s **Potlife at 20°C** 1 h

Application:



Compliant gravity-feed spray gun



HVLV spray gun

Application pressure bar

2

2-3

Nozzle pressure bar

0.7

Nozzle size

1.6-1.8

1.7-1.9

Number of spray coats

3 - 4

Film thickness µm

100-200

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

