

A-C-10

Eco Balance clear coat, fast drying







A brand of BASF –
We create chemistry



Application: AraClass - Eco Balance clear coat for Glasurit waterborne basecoats.

Key Features: Eco effectiveness clear coat - fast drying.
For multiple vertical and horizontal panels, also Spot Repair.

Remarks: Select hardener and reducer according to ambient temperature and size of object to be painted.

3:1:1

	Mixing Ratio	100 % by volume	A-C-10		
	Hardener	33 % by volume	A-H-410, -H-420, -H-430, -H-440 Eco Balance top coat hardener		
	Reducer	33 % by volume	A-R-110, -R-120, -R-130 Eco Balance reducer		
	Spray viscosity at 20°C	DIN 4:	18-21 s	Potlife at 20°C	45 min

Application:		 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	bar	2	2
Nozzle pressure	bar		0.7
Nozzle size		1.3-1.4	1.3
Number of spray coats		1 ½ spray coats (no flash-off between coats required)	
Flash off at 20°C	min	No flash-off before oven drying.	
Film thickness	µm	40-60	
Application Remark		Alternatively: 2 spraycoats with app. 3-5 min. intermediate flash-off between the spraycoats.	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

A-C-10

Eco Balance clear coat, fast drying



A brand of BASF –
We create chemistry



Drying at 20 °C	5-6 h
Drying at 40 °C	30-45 min
Drying at 60 °C	10-15 min



Infrared (short wave)	10 min
------------------------------	--------

Drying Remark Drying times can be influenced by the selection of hardener, reducer and application. A-A-10 or A-A-12 additives can reduce drying times.

Remark Polishing after specified drying time and cooling.



Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.