

Glasurit® Soft face Additive



- Application:** Plasticising additive used in plastics refinishing procedures
- Properties:** Elastified, good miscibility
- Remarks:**
- Addition of 25% by vol.

	Application	Undercoat materials	Topcoat/clear	
	Paint system	S. 3, S. 3a		
	Mixing ratio	4 parts. 285- (100% by vol.) 1 part. 522-111 (25% by vol.)	4 parts 22 VOC 923- (100% by vol.) 1 part 522-111 (25% by vol.)	4 parts 22 VOC MC600 (100% by vol.) 1 part 522-111 (25% by vol.)
	Hardener	4 : 1 : 1 100% by vol. 285- : 522-111 25% by vol. 929-55, -56	2 : 1 + 10 % 100% by vol. 22 VOC /923- : 522-111 50% by vol. 929-31,-33	3 : 1 : 1 100% by vol. 22 VOC MC600 / 923- : 522-111 33% by vol. 929-61, -63, -64
	Reducer	25% by vol. 352-91, -50	10% by vol. 352-91, -50	33% by vol. 352-10, -30, -40
	Spray viscosity DIN 4 at 20°C	16 - 18 s	22 VOC, 22 MC600 923-	20 - 22 s 17 - 18 s
	Potlife at 20 °C	1 - 2 hours	4 hours	
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.7 - 1.9 mm2.0 – 3.0 bar 0.7 bar at the nozzle	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	
	Number of spraycoats	2	2	
	Film thickness	approx. 50 µm	50-60 µm	
	Drying at 20 °C	4 hours	16 hours	
	Drying at 60 °C	40 min.	45 min	
	Infrared (short wave)	8 min.	8 min.	
	Infrared (medium wave)	10 - 15 min.	10 - 15 min.	

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

